

Product Description:

Interpon MetaPrep™ is a powder coating designed as a barrier primer and surfacer for a variety of metal substrates. **Interpon MetaPrep™** is especially suited for porous metal substrates such as hot dipped galvanized steel and alloy castings. Pre-treated substrates are normally coated with 50 to 70 microns of **Interpon MetaPrep™**. This coating offers excellent flow, chemical and salt spray resistance, and resistance to mechanical damage.

Interpon MetaPrep™ is designed to be over coated with an **Interpon** powder coating topcoat such as Interpon 610, Interpon D610 Excel™ and Interpon 700 (for internal applications) to provide enhanced corrosion performance. When cured as per the recommended stoving schedule, **Interpon MetaPrep™** typically displays excellent intercoat adhesion properties with a variety of powder coatings.

Interpon MetaPrep™ is suitable for use as a primer for a variety of liquid topcoats, however it is recommended that pre-qualification tests for intercoat adhesion be carried out prior to use.

Powder properties*:

Chemical type	Epoxy-Polyester
Particle size	Suitable for electrostatic spray
Specific gravity	1.68 +/- 0.01
Storage	Dry cool conditions (below 25°C)
Shelf Life	12 months
Sales code	EE101A (Interpon MetaPrep™ Gold)
Stoving Schedule	(when used as a primer in a two-coat system) 20 mins at 160°C or 15 mins at 170°C or 12 mins at 190°C or 10 mins at 200°C (object temperature)

Test Conditions:

The results shown below are based on mechanical and chemical tests carried out on a two-coat system (primer + Interpon D610 polyester) under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

Substrate	Zinc phosphate coated steel panels
Film Thickness	Primer 50-70 microns: Polyester topcoat 60-80 microns
Stoving	Primer, 10 minutes at 200°C (object temperature): Polyester topcoat, 12 minutes at 200°C (object temperature)

Mechanical tests*:

Adhesion	AS 4506 Section 2.7	Classification 0
Pencil Hardness	AS 4506 Section 2.8	F - minimum
Reverse Impact resistance	AS 4506 Section 2.10	Pass 2.0Nm

Chemical and Durability Tests*:

Salt Spray	ASTM B117	Pass 1500 hours - no corrosion creep more than 2mm from scribe
Humidity Resistance	AS 4506 Section 2.9	Pass 1000 hrs - no blistering or loss of adhesion

Exterior durability	Designed to be used as a primer under suitable powder coating or wet paint topcoats. Exterior durability will then be a function of the topcoat.
----------------------------	--

Pre-treatment:	For optimum coating performance the following pre-treatment is recommended prior to the application of Interpon MetaPrep™ . The pre-treatment should be used in accordance to the supplier's recommendations. A. Aluminium: Multistage chrome chromate or chrome phosphate B. Galvanised Steel: Multistage zinc phosphate or chromate C. Steel: Multistage zinc or iron phosphate
-----------------------	--

Application:	Interpon MetaPrep™ can be applied by manual or automatic electrostatic spray equipment. Unused and over-sprayed powder coating can be reclaimed and recycled through the coating system. Handling of parts coated in Interpon MetaPrep™ should be avoided if possible. If handling is unavoidable, clean lint-free gloves must be worn. It is recommended that the topcoat application be carried out within 24 hours of applying and curing Interpon MetaPrep™ .
---------------------	---

Additional Information:	Akzo Nobel Pty Ltd has a policy not to use TGIC, lead or other heavy metal based pigments in our range of powder coatings.
--------------------------------	--

Safety Precautions:	This product is intended for use only by professional applicators in industrial environments and should not be used without reference to the relevant health and safety data sheet which Akzo Nobel has provided to its customer. If for any reason a copy of the relevant health and safety data sheet is not immediately available the user should contact Akzo Nobel to obtain a copy before using the product. Minimum safety precautions in dealing with all powder coatings are as follows. All dusts are respiratory irritants. Therefore, inhalation of the dust or of the vapours resulting from the cure should be avoided. Take steps to prevent skin contact, but should contact occur, wash skin with soap and water. In case of eye contact flush immediately with clean water and seek medical advice. Dust clouds of any finely divided organic material can be ignited with an electric spark or open flame. Dust and powder should not be allowed to build up on surfaces or ledges. Dust collection equipment should be used which has provision for adequate explosion release. All equipment should be electrically earthed to prevent build up of static. Users are recommended to follow the guidelines laid down in the AS3754:1990 "Safe Application of Powder Coatings by Electrostatic Spraying".
----------------------------	---

Disclaimer:	Unless otherwise agreed by us in writing, any contract to purchase products referred to in this brochure and any advice which we give in connection with the supply of products are subject to our standard conditions of sale. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
--------------------	---

* Typical minimum specifications. Performance may vary slightly between individual products.