

**Collection Elements  
Lanthanum**

**Interpon 310**

**MW305F**

The information given in this datasheet refers to the product **Lanthanum** and should not be construed as referring to other products with in the same range.

**Product Description:** **Lanthanum Interpon 310** is part of Collection Elements specially developed for industrial design.  
**Interpon 310** is a series of polyester resin based thermo-setting powder coatings, without TGIC. The pigments used in the **Interpon 310** series restrict the field of application of this powder coatings class to interior uses.  
**Interpon 310** is designed for interior decoration : metal furniture, shop fittings, shelves, light fittings, ...

<b>Powder Properties:</b>	<b>Chemical type</b>	Polyester
	<b>Specific gravity</b>	1.50
	<b>Storage</b>	Dry cool conditions
	<b>Shelf life</b>	18 months at 30°C
		12 months at 35°C
	<b>Stoving schedule</b> (object temperature)	at 180°C : min 12 mn - max 24 mn
at 200°C : min 8 mn - max 16 mn		
at 210°C : min 4 mn - max 10 mn		

<b>Coating:</b>	<b>Aspect</b>	Fine structured copper matt	
	<b>Test conditions</b>	The results shown are based on tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for advice only, actual performance depends upon the circumstances under which the product is used.	
	Substrate	0.5 mm steel	
	Pre-treatment	Zinc phosphate	
	Film thickness ISO2360	60 microns	
	Stoving	12 minutes at 200°C (object temperature)	
	<b>Mechanical tests</b>		
	Flexibility	ISO 1519	6 mm
	Adhesion	ISO 2409	Gt 0
	Impact	ISO 6272-1	1 kg 0.5 m
	Erichsen Cupping	ISO 1520	> 6 mm
	<b>Chemical and durability test</b>		
	Salt spray	ISO 7253	250 hr pass
	<i>Note test only relates to corrosion resistance</i>		
	Constant humidity	ISO 6270	1000 hr pass
<i>Note test only relates to corrosion resistance</i>			
Chemical resistance	See Post Application		

**Industrial application conditions:** **Pre-treatment**  
Aluminium, steel or Zintec surfaces must be clean and free from grease.  
Iron phosphate and lightweight zinc phosphating of ferrous metals improves corrosion resistance.  
Aluminium surfaces may require a suitable chromate conversion, chrome free pre-treatment or flash anodising for certain applications.  
Galvanised steel may require zinc or chromate conversion or sweep blasting.  
*Detailed advice should be sought from the pre-treatment supplier*  
**Recommended film thickness**  
60 - 90 microns

**Application**

Lanthanum can be applied by corona electrostatic or tribostatic equipment.

**However the aspect obtained by tribostatic equipment may vary when compared to electrostatic application and/or our colour card.**

In all application processes the aspect obtained is subject to variation, depending on the method of application (type of gun, nozzle, pot etc) and the shape/type of component.

We recommend that the actual application parameters are adapted and adjusted depending on the type of component and with each powder batch in order to give a finish in accordance with our colour card.

The following procedure is given as a guideline when using these finishes :

We recommend the use of flat jet spray nozzles.

To ensure powder homogeneity empty the boxes totally into the tray or feed hopper.

Only one spray run and one batch of powder should be used for components which are to be used in the same project.

For manual application it is essential to ensure that an even film thickness is applied and in all instances sinusoidal gun movements should be avoided.

**Recycling**

Possible up to 30% of reclaimed powder. Panels should be sprayed to ensure continuity of finish.

**Post application :**

**Contact with Chemical Agents**

Contact, even of a short duration with certain household products and chemicals, can cause irreversible changes in the gloss and appearance. We recommend that a test is carried out on a non-visible area before using these types of products on this coating. This finish is sensitive to aggressive environments.

**Safety Precautions :**

Please consult the Material Safety Datasheet (PC010)

**FOR PROFESSIONAL USE ONLY**

**IMPORTANT NOTE** The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advice given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel.

**Head Office**