

Interpon HF

BA003G

Product Description: **BA003G** is a highly chemically resistant powder coating formulated for use as a lining for metal drums used for the bulk transportation of general industrial chemicals. It is fully FDA compliant. Long term exposure to ultraviolet light or exterior weathering is not recommended.

Powder Properties:	Colour	Off White
	Gloss	90±5% (60° head) ASTM D523-89
	Particle size	Suitable for electrostatic or tribostatic application
	Specific gravity	1.5±0.05 g/cm ³
	Storage	Dry cool conditions below 25°C
	Stoving schedule (object temperature)	10 minutes at 200°C
		6 minutes at 230°C

Test Conditions: The results shown below are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

Mechanical Tests:	Substrate	0.8mm, 1.0mm, 1.2mm, 1.5mm steel	
	Pretreatment	Iron Phosphate	
	Film Thickness	60-70 microns	
	Adhesion	BS EN ISO2409 (2mm Crosshatch)	Gt 0
	Erichsen	ISO1520	7mm
Chemical Resistance:	Impact	BS3900-E3	8 joules forward or reverse
	Conical Mandrel	ISO6860	Pass 10mm

Chemical Resistance: **BA003G** has been formulated to have resistance to a wide range of general industrial chemicals and foodstuffs. For more information regarding specific chemicals and/or foodstuffs resistance contact Akzo Nobel.

Pretreatment:	For more information regarding specific substrates and applications for Interpon HF - BA003G contact Akzo Nobel.
Application:	Interpon HF - BA003G can be applied either electrostatically or tribostatically. Unused powder can be reclaimed using suitable equipment and recycled through the coating system.
Safety Precautions:	This product is intended for use only by professional applicators in industrial environments and should not be used without reference to the relevant health and safety data sheet which Akzo Nobel has provided to its customer. If for any reason a copy of the relevant health and safety data sheet is not immediately available the user should contact Akzo Nobel to obtain a copy before using the product. Minimum safety precautions in dealing with all powder coatings are as follows: All dusts are respiratory irritants. Therefore, inhalation of the dust or of the vapours resulting from the cure should be avoided. Take steps to prevent skin contact, but should contact occur, wash skin with soap and water. In case of eye contact flush immediately with clean water and seek medical advice. Dust clouds of any finely divided organic material can be ignited with an electric spark or open flame. Dust and powder should not be allowed to build up on surfaces or ledges. Dust collection equipment should be used which has provision for adequate explosion release. All equipment should be electrically earthed to prevent build up of static. Users are recommended to follow the guidelines laid down in the "Code of Safe Practices" issued by the British Coatings Federation, copies of which are available on request.

Disclaimer:	The information given in this sheet is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. Whilst we endeavour to ensure that all advice we give about the product (whether in this sheet or otherwise) is correct we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of the use of the product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
--------------------	--