

**Collection Elements  
Sulfur**

**Interpon 620**

**OZ603I**

The information given in this datasheet refers to the product **Sulfur** and should not be construed as referring to other products with in the same range.

**Product Description:**

**Sulfur Interpon 620** is part of Collection Elements specially developed for industrial design.

**Interpon 620** is a series of polyester resin based thermo-setting powder coatings, without TGIC.

Polyester powder coatings have good U.V. and weathering resistance.

Offering good mechanical strength and good weathering resistance, this class of polyester powder coatings is used both for interior decorating, metal furniture, shop design, ... and for coating parts for outside exposure, lights, garden and street furniture, etc...

**Powder Properties:**

<b>Chemical type</b>	Polyester
<b>Density</b>	1.22
<b>Storage</b>	Dry cool conditions
<b>Shelf life</b>	18 months at 30°C 12 months at 35°C
<b>Stoving schedule</b> (object temperature)	at 190°C : min 15 mn - max 26 mn at 200°C : min 10 mn - max 20 mn at 210°C : min 8 mn - max 16 mn

**Coating :**

<b>Aspect</b>	Glossy gold toned clear	
<b>Test conditions</b>	The results shown are based on tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for advice only, actual performance depends upon the circumstances under which the product is used.	
Substrate	0.5 mm steel	
Pre-treatment	Zinc phosphate	
Film thickness ISO2360	70 microns	
Stoving	15 minutes at 200°C (object temperature)	
<b>Mechanical tests</b>		
Flexibility	ISO 1519	6 mm
Adhesion	ISO 2409	Gt 0
Impact	ISO 6272-1	1 kg 0.5 m
Erichsen Cupping	ISO 1520	> 6 mm
<b>Chemical and durability test</b>		
Salt spray	ISO 7253	250 hr pass
<i>Note test only relates to corrosion resistance</i>		
Constant humidity	ISO 6270	1000 hr pass
<i>Note test only relates to corrosion resistance</i>		
Artificial weathering	QUV B 313 200 hours	>50% Gloss retention
Chemical resistance	See Post Application	

**Industrial application conditions :**

<b>Pre-treatment</b>
Aluminium, steel or Zintec surfaces must be clean and free from grease. Iron phosphate and lightweight zinc phosphating of ferrous metals improves corrosion resistance. Aluminium surfaces may require a suitable chromate conversion, chrome free pre-treatment or flash anodising for certain applications. Galvanised steel may require zinc or chromate conversion or sweep blasting. <i>Detailed advice should be sought from the pre-treatment supplier</i>
<b>Recommended film thickness</b>
60 - 80 microns A good effect is linked with the recommended thickness.

---

**Application**

**Sulfur** can be applied by corona electrostatic or tribostatic equipment.

**Sulfur** is a tinted clearcoat and can be used directly on surfaces or to overcoat a powder base colour.

Reproduction of the finish and shade varies in accordance with the underlying surfaces, the type of undercoat and the applied film thickness of the **Sulfur**.

Edge effects may be visible.

To ensure good final results. The surface to be coated must be as uniform as possible.

When using **Sulfur** as a topcoat the application to the base coat should be done immediately on the same site. The maximum allowable period between coats is 2 hours.

For gas oven curing, please check if colour is acceptable.

In all application processes the aspect obtained is subject to variation, depending on the method of application (type of gun, nozzle, pot etc) and the shape/type of component.

We recommend that the actual application parameters are adapted and adjusted depending on the type of component and with each powder batch in order to give a finish in accordance with our colour card.

---

**Recycling**

Powder can be recycled using suitable reclaim equipment.

---

**Post application :**

**Contact with Chemical Agents**

Contact, even of a short duration with certain household products and chemicals, can cause irreversible changes in the gloss and appearance. We recommend that a test is carried out on a non-visible area before using these types of products on this coating.

---

**Safety Precautions:**

Please consult the Material Safety Datasheet (PC111)

**Disclaimer:**

The information given in this sheet is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. Whilst we endeavour to ensure that all advice we give about the product (whether in this sheet or otherwise) is correct we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of the use of the product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.