

Product Datasheet



BU Powder Coatings

Interpon EC

AkzoNobel
Tomorrow's Answers Today

Product Description	<p>Interpon EC is a high quality powder formulated to have excellent anti-graffiti and stain resistance properties with good aesthetic appearance.</p> <p>Interpon EC is suitable for outdoor use and architectural applications. Aerosol paints can be easily removed using xylene, acetone or trichloroethylene.</p> <p>Interpon EC is available in a range of colours and as a transparent clear and can be custom matched to user's requirements.</p>	
Powder Properties	Chemical type	Reinforced Polyurethane
	Particle Size	Suitable for electrostatic spray
	Gloss	Gloss & Semi-gloss
	Specific gravity	1.2-1.9 g/cm ³ (depending on colour)
	Storage	Dry cool conditions below 25°C
	Shelf life	6 months
	Stoving schedule (object temperature)	20 minutes at 190°C 15 minutes at 200°C
Test Conditions	<p>The results shown below are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.</p>	
	Substrate	Mechanical tests: 0.6mm degreased steel Chemical tests: 0.6mm Zn/Mn phoshated steel
	Film Thickness	60 - 70 microns
	Stoving	20 minutes at 190°C (object temperature)
Mechanical Tests	Adhesion	ISO2409 DIN53151(2mm crosshatch) Gt 0 Gt 0 >95%
	Erichsen Cupping	ISO1520 >4 mm
	Hardness	ISO15814 2H to 3H
	Impact	ISO/TR6272 Pass 2.5 Joule D/R Pass 25Kg/cm D/R
	Flexibility	ISO1519 (Cylindrical Mandrel) ISO6860 (Conical Mandrel) Pass 3/16" Pass 3mm
Chemical Tests	Salt Spray	UNI5687/73 (>500 hours) With creepage from scribe ≤3mm
	Constant Humidity	UNI8744 (>1000 hours) Without blistering
	Gasoline, Diesel fuel & Ethanol	60 mins @ 25°C Pass - no blistering or change in appearance
	Xylene, Mobil brake Fluid & Acetone	10 mins @ 25°C Pass - no blistering, or change in appearance
	Acetone/Ethyl acetate (1:1) & Acetone	100 rubs @ 25°C Pass - no blistering, or change in appearance
	0.1N Hydrochloric acid & 0.1N Sodium Hydroxide	4 hours @ 60°C Pass - no blistering or change in appearance

Anti-graffiti Resistance

<u>Type</u>	<u>Cleaning Fluid</u>
Enamel Spray	A, C, D
Water-based Marker	O
Permanent Marker	A, B, C, D, E
Lipstick	O
Shoe Polish	O

Key:

- A 90% denatured alcohol
- B 1:1 mixture of denatured alcohol & detergent
- C Acetone
- D Trichloroethylene
- E Tetrachloroethane
- O Rub with cloth

Pretreatment

For more information regarding specific substrates and applications for **Interpon EC** contact Akzo Nobel.

Application

Interpon EC powders can be applied by manual or automatic electrostatic spray equipment. Unused powder can be reclaimed using suitable equipment and recycled through the coating system.

Safety Precautions

Please consult the Material Safety Datasheet (MSDS)

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advice given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel