

Product Datasheet

2000 Series



BU Powder Coatings

AkzoNobel

Tomorrow's Answers Today

Interpon D2525 Sablé

The information given in this datasheet is generic for the range **Interpon D2525 Sablé**. Specific products within the range can vary from the generic. For these products individual product datasheets are available.

Product Description

Interpon D2525 Sablé is a series of ultra-durable powder coatings specifically formulated without TGIC, with sand-blasted aspect for use on architectural aluminium components. Providing new levels of weathering resistance **Interpon D2525** surpasses the performance of leading architectural powders. It offers significantly higher gloss retention and resistance to colour change combined with maximum film integrity to ensure long term cosmetic and functional protection.

The **Interpon D2525** range was the first to be awarded the prestigious Qualicoat, Class 2 approval for ultra durable powder coatings and conforms to the requirements of EN12206 and EN13438 (high durability systems) and AAMA 2604-5.

Powder Properties

Chemical type	Polyester
Gloss	5 - 15
Particle Size	Suitable for electrostatic spray
Specific gravity	1.2 – 1.9 g/cm ³ depending on colour
Storage	Dry, cool conditions
Shelf life	24 months below 30°C peak temperature 12 months below 35°C peak temperature
Sales Code	Y Series
Stoving schedule (object temperature)	25-45 minutes at 180°C 12-24 minutes at 200°C 8-14 minutes at 210°C

Test Conditions

The results shown below are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

Appearance	Sand blasted matt
Substrate	Aluminium (0.5-0.8mm Al Mg1)
Pretreatment	Chromate
Film Thickness	70 – 90 microns
Stoving	10 minutes at 200°C (object temperature)

Mechanical Tests

Dry Adhesion	ISO2409	Pass Gt 0
Ericksen Cupping	ISO1520 and Qualicoat, Class 2	Pass
Dry Film Hardness	ISO2815 (Buchholz)	Pass > 80
Impact	ASTM D2794 and Qualicoat, Class 2	Pass
Flexibility	ISO1519 and Qualicoat, Class 2	Pass

Chemical and Durability Tests

Salt Spray	ISO 7253	Pass at 3000 hours - no corrosion area more than 1.6mm from scribe Minimum Blister Rating 8
Acetic Acid Salt Spray	ISO9227	Pass at 1000 hours <16 mm ² corrosion/10cm
Constant Humidity	ISO6270	Pass at 1000 hours - no corrosion area > 1mm from scribe
Sulphur Dioxide Permeability	ISO3231 (Kesternich) Pressure Cooker EN12206-1.2004 (5.1)	Pass – no blistering, loss of gloss or discoloration Pass – no defects after 1 hour
Chemical Resistance	Generally good resistance to acid, alkalis and oils at normal temperatures	

Interpon D2525 Sablé

Exterior Durability	Exceeds Qualicoat Class 2 requirements after 3 years Florida Exposure
Colour Stability at Elevated Temperatures	Excellent

Pretreatment	For maximum protection it is essential to pretreat components prior to the application of Interpon D2525 Sablé . Aluminium components should receive a full multi-stage chromate conversion coating or suitable chrome-free pre-treatment or suitable chrome-free pretreatment to clean and condition the substrate. Detailed advice should be sought from the pre-treatment supplier.
Application	Interpon D2525 Sablé powders can be applied by manual electrostatic spray equipment. Unused powder can be reclaimed using suitable equipment and recycled through the coating system. Please contact AkzoNobel for further details as to the correct mixing ratio for virgin/reclaim powder.
Safety Precautions	Please consult the Material Safety Datasheet (PC010)

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advice given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.