

**Collection Elements
Chlorine**

Interpon 610

MW014F

The information given in this datasheet refers to the product **Chlorine** and should not be construed as referring to other products with in the same range.

Product Description: **Chlorine Interpon 610** is part of Collection Elements specially developed for industrial design.
Interpon 610 is a series of polyester resin based thermo-setting powder coatings, without TGIC.

Polyester powder coatings have good U.V. and weathering resistance.

Offering good mechanical strength and good weathering resistance, this class of polyester powder coatings is used both for interior decorating, metal furniture, shop design, and for coating parts for outside exposure, lights, garden and street furniture, etc...

Powder Properties:	Chemical type	Polyester
	Specific Gravity	1.58
	Storage	Dry cool conditions
	Shelf life	18 months at 30°C 12 months at 35°C
	Stoving schedule (object temperature)	at 180°C : min 12 mn - max 30 mn at 200°C : min 8 mn - max 20 mn at 210°C : min 4 mn - max 16 mn

Coating :	Aspect	Bottle Green gloss pearl	
	Test conditions	The results shown are based on tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for advice only, actual performance depends upon the circumstances under which the product is used.	
	Substrate	0.5 mm steel	
	Pre-treatment	Zinc phosphate	
	Film thickness ISO2360	70 microns	
	Stoving	15 minutes at 200°C (object temperature)	
	Mechanical tests		
	Flexibility	ISO 1519	5 mm
	Adhesion	ISO 2409	Gt 0
	Impact	ISO 6272-1	1 kg 0.5 m
	Erichsen Cupping	ISO 1520	5 mm
	Chemical and durability test		
	Salt spray	ISO 7253	250 hr pass
	<i>Note test only relates to corrosion resistance</i>		
	Constant humidity	ISO 6270	1000 hr pass
<i>Note test only relates to corrosion resistance</i>			
Artificial weathering	QUV B 313 200 hours	>50% Gloss retention	
Chemical resistance	See Post Application		

Industrial application conditions :	Pre-treatment	Aluminium, steel or Zintec surfaces must be clean and free from grease. Iron phosphate and lightweight zinc phosphating of ferrous metals improves corrosion resistance. Aluminium surfaces may require a suitable chromate conversion, chrome free pre-treatment or flash anodising for certain applications. Galvanised steel may require zinc or chromate conversion or sweep blasting. <i>Detailed advice should be sought from the pre-treatment supplier</i>
	Recommended film thickness	60 - 80 microns A good effect is linked with the recommended thickness.

Application

Chlorine can be applied by corona electrostatic or tribostatic equipment.
However the aspect obtained by tribostatic equipment may vary when compared to electrostatic application and/or our colour card

In all application processes the aspect obtained is subject to variation, depending on the method of application (type of gun, nozzle, pot etc) and the shape/type of component.

We recommend that the actual application parameters are adapted and adjusted depending on the type of component and with each powder batch in order to give a finish in accordance with our colour card.

The following procedure is given as a guideline when using these finishes:

To ensure powder homogeneity empty the boxes totally into the tray or feed hopper. Only one spray run and one batch of powder should be used for components which are to be used in the same project.

For manual application it is essential to ensure that an even film thickness is applied and in all instances sinusoidal gun movements should be avoided.

Recycling

Powder can be recycled using suitable reclaim equipment.

Post application :

Contact with Chemical Agents

Contact, even of a short duration with certain household products and chemicals, can cause irreversible changes in the gloss and appearance. We recommend that a test is carried out on a non-visible area before using these types of products on this coating.

Safety Precautions:

Please consult the Material Safety Datasheet (PC010)

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advice given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel.

Head Office